

## Properties

Polytec EP 610-2 is a transparent, two-component epoxy adhesive of very low viscosity and high flexibility.

Polytec EP 610-2 is used for stress-free bonding of large optical components with different CTE's.

It is suggested for applications in optics, fiber optics, optoelectronics, medical and semiconductor technology.

The material can be applied via dispensing, jet-dispensing and manual application.



## Processing

- For two-component products the components A and B should be mixed carefully within the specified mixing ratio.
- For filled products both components should be homogenized carefully prior mixing, in order to prevent a possible settling of the filler.
- Processing should be carried out rapidly after mixing the components; as an indication the pot life can be used.
- Surfaces should be clean, thus free of dirt, grease, oil, dust or process chemicals.
- One-component products can be applied directly and are not subject to a pot life (except pre-mixed/frozen products).
- Please take notice of respective minimum curing temperature and time.
- For Safety information please refer to the respective Material Safety Data Sheet.

# Polytec EP 610-2

## Unfilled Epoxy Adhesive

### Technical Data

# Polytec EP 610-2

Properties in uncured state	Method	Unit	Technical Data
Chemical basis	-	-	Epoxy
No. of components	-	-	2
Mixing ratio (weight)	-	-	100:50
Mixing ratio (volume)	-	-	-
Pot life at 23°C	TM 702	h	ca. 6
Storage Stability at 23°C	TM 701	Months	12
Consistency	TM 101	-	Flowable liquid
Density Mix	TM 201.2	g/cm <sup>3</sup>	1.07
Density A-Part	TM 201.2	g/cm <sup>3</sup>	1.15
Density B-Part	TM 201.2	g/cm <sup>3</sup>	0.95
Viscosity Mix 84 s <sup>-1</sup> at 23°C	TM 202.1	mPa·s	830
Viscosity A-Part 84 s <sup>-1</sup> at 23°C	TM 202.1	mPa·s	2 000
Viscosity B-Part 84 s <sup>-1</sup> at 23°C	TM 202.1	mPa·s	49

Properties in cured* state	Method	Unit	Technical Data
Color	TM 101	-	Translucent
Hardness* (Shore A / Shore D)	DIN EN ISO 868	-	ca. 80 / 30
Temperature resistance continuous	TM 302	°C	-55 / +150
Temperature resistance short term	TM 302	°C	-55 / +250
Degradation Temperature	TM 302	°C	ca. +300
Glass Transition Temperature (T <sub>g</sub> )	TM 501	°C	ca. 10
Coefficient of thermal expansion (<T <sub>g</sub> )	ISO 11359-2	ppm	-
Coefficient of thermal expansion (>T <sub>g</sub> )	ISO 11359-2	ppm	-
Thermal conductivity	-	W/m·K	-
Elasticity modulus*	TM 605	N/mm <sup>2</sup>	<10
Tensile Strength*	TM 605	N/mm <sup>2</sup>	ca. 2.6
Lap shear strength** (Al/Al)	TM 604	N/mm <sup>2</sup>	ca. 9.3
Elongation at break*	TM 605	%	ca. 80
Water absorption 24 h, 23°C	TM 301	%	-

\*The data above has been determined with samples cured 2h at 100 °C. Please notice, by varying the curing temperature these properties can be influenced to some extent. For example a curing at 150 °C may increase mechanical properties.

\*\*2h@100 °C+1h@150 °C

# Polytec EP 610-2

Curing*	Method	Unit	Technical Data
Minimum curing temperature		°C	15
Curing time at 23°C		d	2 - 7
Curing time at 80°C		min	-
Curing time at 100°C		min	90
Curing time at 150°C		min	-

\*Curing temperatures refer to the temperature in the respective bond line. When choosing the respective curing conditions, the time needed to heat the substrate has to be considered. Depending on the type of heat source (convection oven, hot stamp, heating plate) the heat input may vary.

## Standard pack sizes:

250 g, 500 g

1 kg

Customized packaging

Also available as pre-mixed, degassed and frozen product

## Please note:

The information listed above is typical data based on tests and is believed to be accurate. Polytec PT makes no warranties (expressed or implied) as to their accuracy. The data listed above does not constitute specifications. The processing (particularly the curing conditions) of the material, the process control, and the variety of different applications at various customers are not under Polytec PT's control. Therefore, Polytec PT will not be liable for concrete results in any specific application or in any connection with the use of this product. The curing conditions have a major effect on the properties of the cured material. Therefore, it is highly recommended to keep the curing schedule – once established - under tight control. With the release of this data sheet all former data sheets will be null and void.

Subject to alteration.

**Polytec PT GmbH**  
**Polymere Technologien**

**Ettlinger Straße 30**  
**76307 Karlsbad**  
**Germany**  
**Phone +49 (0)7202 706-3500**

**info-pt@bostik.com**  
**www.polytec-pt.de**

**Polytec PT GmbH**  
**Polymere Technologien**  
**plant Maxdorf**

**Bahnhofstraße 1**  
**67133 Maxdorf**  
**Germany**

**info-pt@bostik.com**  
**www.polytec-pt.de**