



Technical Data Sheet

DOWSIL™ SE 4486 Thermally Conductive Adhesive

FEATURES & BENEFITS

- One part material
- Semi-flowable
- Fast tack-free time
- Good adhesion
- Thermally conductive

COMPOSITION

- Thermally conductive filler
- Polydimethylsiloxane adhesive

One part, white, moisture cure, thermally conductive silicone adhesive

APPLICATIONS

DOWSIL™ SE 4486 Thermally Conductive Adhesive is designed to provide efficient thermal transfer for the cooling of modules, including home appliance devices.

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
One part or Two Part	-	One
Color	-	White
Viscosity	cP	19,600
	Pa-sec	19.6
	mPa-sec	19,600
Fluidity	mm	60
	in	2.32
Specific Gravity (Cured)	-	2.6
Tack-Free Time at 25°C	minutes	4
Tensile Strength	psi	570
	mPa	3.9
	kg/cm ²	40
Elongation	%	43
Durometer Shore A (JIS*)	-	81
Unprimed Adhesion - Lap Shear, Glass to Glass	psi	240
	mPa	1.65
	N/cm ²	165
Thermal Conductivity	W/mK	1.6
	btu/hr-ft-°F	0.92

*JIS: Japanese Industry Standard.

DESCRIPTION

One-part RTV-cure thermally conductive materials cure with moisture exposure to produce durable, relatively low-stress elastomer with a noncorrosive by-product. PCB system assemblies are continually designed to deliver higher performance. Especially in the area of consumer devices, there is also a continual trend towards smaller, more compact designs. In combination these factors typically mean that more heat is generated in the device. Thermal management of PCB system assemblies is a primary concern of design engineers. A cooler device allows for more efficient operation and better reliability over the life of the device. As such, thermally conductive compounds play an integral role here. Thermally conductive materials act as a thermal “bridge” to remove heat from a heat source (device) to the ambient via a heat transfer media (i.e. heat sink). These materials have properties such as low thermal resistance, high thermal conductivity, and can achieve thin Bond Line Thicknesses (BLTs) which can help to improve the transfer of heat away from the device.

SUBSTRATE TESTING

To ensure maximum bond strength for adhesives on a particular substrate, 100 percent cohesive failure of the adhesive in a lap shear or similar adhesive strength test is needed. This ensures compatibility of the adhesive with the substrate being considered. Also, this test can be used to determine minimum cure time or to detect the presence of surface contaminants such as mold release agents, oils, greases and oxide films.

PROCESSING/CURING

The one-part moisture-cure adhesives are generally cured at room temperature and in a range of 0 to 80 percent relative humidity. Greater than 90 percent of their full physical properties should be attained within 4 to 7 hours depending on the product chosen. These materials are not typically used for highly confined or deep section cures. Materials will generally cure about 0.25 inch (6.35 mm) per 7 days.

ADHESION

Dow silicone adhesives are specially formulated to provide unprimed adhesion to many reactive metals, ceramics and glass, as well as to selected laminates, resins and plastics. However, good adhesion cannot be expected on non-reactive metal substrates or non-reactive plastic surfaces such as Teflon[®], polyethylene or polypropylene. Special surface treatments such as chemical etching or plasma treatment can sometimes provide a reactive surface and promote adhesion to these types of substrates. Dow primers can be used to increase the chemical activity on difficult substrates. For best results, the primer should be applied in a very thin, uniform coating and then wiped off after application. After application, primers should be thoroughly air dried prior to application of the silicone elastomer. Alternatively, use a low-viscosity primerless adhesive to pot your components. Poor adhesion can be experienced on plastic or rubber substrates that are highly plasticized, since the mobile plasticizers act as release agents. Small-scale laboratory evaluation of all substrates is recommended before production trials are made. In general, increasing the cure temperature and/or cure time will improve the ultimate adhesion.

USEFUL TEMPERATURE RANGES

For most uses, silicone adhesives should be operational over a temperature range of -45 to 200°C (-49 to 392°F) for long periods of time. However, at both the low and high temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible for most products, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the durability of the cured silicones is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.

SOLVENT EXPOSURE

In general, the product is resistance to minimal or intermittent solvent exposure, however best practice is to avoid solvent exposure altogether.

USABLE LIFE AND STORAGE

The product should be stored in its original packaging with the cover tightly attached to avoid any contamination. Store in accordance with any special instructions listed on the product label. The product should be used by the indicated Exp. Date found on the label.

UNRESTRICTED – May be shared with anyone

®™ The DOW Diamond and DOWSIL are trademarks of The Dow Chemical Company

Teflon is a registered trademarks of E. I. du Pont de Nemours and Company or its affiliates.

DOWSIL™ SE 4486 Thermally Conductive Adhesive

© 2017 The Dow Chemical Company. All rights reserved.

**HANDLING
PRECAUTIONS
PRODUCT SAFETY
INFORMATION REQUIRED FOR
SAFE USE IS NOT INCLUDED IN
THIS DOCUMENT. BEFORE
HANDLING, READ PRODUCT
AND SAFETY DATA SHEETS
AND CONTAINER LABELS FOR
SAFE USE, PHYSICAL AND
HEALTH HAZARD
INFORMATION. THE SAFETY
DATA SHEET IS AVAILABLE ON
THE DOW WEBSITE AT
WWW.CONSUMER.DOW.COM,
OR FROM YOUR DOW SALES
APPLICATION ENGINEER, OR
DISTRIBUTOR, OR BY CALLING
DOW CUSTOMER SERVICE.**

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, www.consumer.dow.com or consult your local Dow representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use.

Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT
PERMITTED BY APPLICABLE
LAW, DOW SPECIFICALLY
DISCLAIMS ANY OTHER
EXPRESS OR IMPLIED
WARRANTY OF FITNESS FOR A
PARTICULAR PURPOSE OR
MERCHANTABILITY.**

**DOW DISCLAIMS LIABILITY
FOR ANY INCIDENTAL OR
CONSEQUENTIAL DAMAGES.**

HOW CAN WE HELP YOU TODAY?

Tell us about your performance, design, and manufacturing challenges. Let us put our silicon-based materials expertise, application knowledge, and processing experience to work for you.

For more information about our materials and capabilities, visit **www.consumer.dow.com**.

To discuss how we could work together to meet your specific needs, go to **www.consumer.dow.com** for a contact close to your location. Dow has customer service teams, science and technology centers, application support teams, sales offices, and manufacturing sites around the globe.

www.consumer.dow.com

