

MOLYKOTE® G-2001 High Speed Bearing Grease

Lithium-thickened bearing grease based on synthetic hydrocarbon

Features & benefits

- Wide service-temperature range
- Usable for high speeds
- Excellent low-temperature properties
- Excellent temperature-consistency profile

Composition

- Synthetic base oil
- Lithium-calcium thickener
- Corrosion inhibitors

Applications

High-speed bearings, spindles, fast-moving positioners, moulding cutters, chemical industry and paper processing.

Description

MOLYKOTE® G-2001 High Speed Bearing Grease is a synthetic-oil-based grease thickened by a lithium-calcium system. MOLYKOTE® G-2001 Grease offers excellent low-temperature performance. MOLYKOTE® G-2001 Grease provides premium protection against wear and corrosion. The absence of solid lubricants makes MOLYKOTE® G-2001 Grease well-suited for small- to medium-sized rolling element bearings at high speeds.

How to use

Apply using conventional grease application methods (i.e., clean brush, grease gun, and manual or automated dispensing equipment).

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

| Standard ⁽¹⁾ | Test | Unit | Result |
|-------------------------------|--|-----------------------|----------------------|
| | Color | | Beige |
| | Base oil type | | PAO |
| | Thickener type | | Lithium-calcium soap |
| Consistency, viscosity | | | |
| DIN 51 818 | Consistency | NLGI Class | 2 |
| ISO 2137 | Worked penetration | mm/10 | 265-295 |
| DIN 51 562 | Base oil viscosity at 40°C | mm ² /s | 35 |
| DIN 51 562 | Base oil viscosity at 100°C | mm ² /s | 6 |
| Temperature | | | |
| | Service temperature range | °C | -50 to +130 |
| | | °F | -58 to +266 |
| ISO 2176 | Drop point | °C (°F) | >190 (>374) |
| DIN 51 805 | Flow pressure at -35°C | mbar (psi) | 450 (6.5) |
| DIN 51 805 | Flow pressure at -50°C | mbar (psi) | <1,400 (<20.3) |
| ASTM D1478-63 | Low-temperature torque | | |
| | -20°C starting/running | Nm x 10 ⁻³ | 53/24 |
| | -40°C starting/running | Nm x 10 ⁻³ | 103/24 |
| Oil separation | | | |
| DIN 51 817 | Oil separation (18 hrs/40°C) | Mass-% | <2.5 |
| | Evaporation loss (30 hrs/ 100°C) | Mass-% | 0.6 |
| DIN 51 808 | Oxidation stability, pressure drop (100 hrs/ 99°C) | bar | <0.8 |

⁽¹⁾DIN: Deutsche Industrie Norm. ISO: International Standardization Organization. ASTM: American Society for Testing and Materials.

Typical properties (continued)

| Standard ⁽¹⁾ | Test | Unit | Result |
|---|----------------------------------|-----------------------|---------|
| Load-carrying capacity, wear protection, speed | | | |
| DIN 51 821-1 | FE9 (6,000 rpm / 1,500 N/ 130°C) | F ₅₀ [hrs] | 175 |
| DIN 51 350-4 | Four ball tester weld load | N | 1,500 |
| DIN 51 350 | Wear scar under 400 N load | mm | 0.69 |
| | DN value (D _R x rpm) | | 900,000 |
| DIN 51 802 | SKF EMCOR | | 0-0 |
| ASTM D4048 | Copper corrosion (24 hrs/100°C) | Level | 1 |

⁽¹⁾DIN: Deutsche Industrie Norm. ISO: International Standardization Organization. ASTM: American Society for Testing and Materials.

Usable life and storage

When stored between 0 and 40°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

Packaging

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 2003-2020 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.