

IQ-BOND 5132-CE

Flexibilized, Low-Stress, Electrically-Conductive, 1-Komponent Adhesive

Pre-Mixed, One Component, Solvent-Free, Hybrid-Epoxy Adhesive

Product Description:

IQ-BOND 5132-CE is a solvent-free, heat curable, one-component, pre-mixed, electrically-conductive adhesive, developed for applications where flexibility is required. IQ-BOND 5132-CE combines low stress with good adhesion on nearly all surfaces.

The rheology of IQ-BOND 5132-CE allows both dispensing, printing, as well as stamping processes. It has a high adhesion strength to substrate finishes commonly used in microelectronics applications.

IQ-BOND 5132-CE, in contrast to many other epoxy adhesives, is based on special selected flexibilized chemistry, making it an ideal solution for bonding applications of dissimilar materials with significant differences in CTE (coefficient of thermal expansion).

When fully cured, IQ-BOND 5132-CE is resistant to moisture, cleaning agents and dilute acids and bases. Its chemistry has been selected to combine flexibility with great adhesion, making it a preferred solution for bonding thermally mismatched substrates such as ceramic to aluminum, or ceramic to copper.

The chemistry of IQ-BOND 5132-CE allows operation temperatures between -50°C and +200°C.

IQ-BOND 5132-CE is a solvent-free, 100% solids material and RoHS / REACH compliant.

For optimum curing performance, it's recommended to do the cure process in a conveyor belt oven. When curing IQ-BOND 5132-CE in a convection oven, it is recommended to apply a longer curing time for optimum adhesion properties.

For cleaning un-cured IQ-BOND 5132-CE from stencils, screens, squeegee, or other equipment, the use of IQ-CLEANER 9500 is recommended.

IQ-BOND 5132-CE is the electrically conductive version of IQ-BOND 2132.

Product Properties:

- Appearance: Silver paste
- Chemistry: Hybrid epoxy
- Odor: Faint



- Mix-Ratio: Not Applicable – pre-mixed “one component” adhesive
- Fineness: < 40 µm
- Viscosity: ~ 160.000 mPa.s (CP52, RVII – at 25°C / 0,5 rpm)
- Density ~ 3,1 gr/cc
- Adhesion Strength: > 200 kg/cm²
- Hardness: ~ 50 shore D / 95 shore A
- Glass Transition Temp. Tg: ~25°C
- Volume Resistivity: ~ 5 x 10⁻⁴ Ohm.cm (after cure 60 minutes 150°C)
- % Ash residue: ~ 74 +/- 1
- Thermal Conductivity: ~ 4,5 W/m.K
- Cure Speed*:
 - 15 minutes @ 175°C
 - 60 minutes @ 150°C
 - 90 minutes @ 120°C

For good mechanical strength, cure according above conditions is recommended. The final bond strength will depend on the residence time at the given cure temperature. Typically, a higher curing temperature, as well as a longer cure time will result in higher adhesion strength, and improved polymer crosslinking.

Processing parameters:

IQ-BOND 5132-CE is suitable for most dispensing systems. Prior to use, it's advised to let the adhesive IQ-BOND 5132-CE equilibrate to room temperature.

Storage stability:

When stored at temperatures below -20°C, in closed and sealed containers, the storage stability of IQ-BOND 5132-CE is 6 months from date of production. At temperatures < -40°C, the shelflife is 12 months.

At room temperature, IQ-BOND 5132-CE has a worklife / potlife of ~ 12 hours.

Attention:

The technical information contained herein should not be used in the preparation of specifications, as it's intended for reference only. Please contact your local sales representative for support. The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Roartis specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Roartis products and services. Roartis specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license. We recommend that each prospective user tests his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more European or foreign patents or patent applications. The information contained in this data sheet corresponds to the present state of our knowledge ; it is intended for your guidance but we are not bound by it since we are not in a position to exercise control over the manner in which our products are used. Moreover, the attention of the user is drawn to the risks that could possibly occur should a product be used for an application other than that for which it is intended.

